

LEIGHTON

Cemento / Concrete

 **cesantoni**
C E R Á M I C A



 Tecnología Digital
Cesantoni

Ficha Técnica Technical Information

SUPER GRES / SUPER GRES Tile

Link: Pasta blanca vs. Pasta Roja

100%
Pasta
Blanca

Formato / Size:

60 x 120 cm Rectificado / 23,6" x 47,2" Rectified

 **SG**
SUPER GRES

15 CARAS

15 FACES

IV
PEI


TTM / B

INTERIORES

INTERIOR

BAÑOS

BATHROOM

COCINA

KITCHEN

EXTERIORES

EXTERIOR

	Espesor / Thickness	11 mm	
	Separación de boquilla / Grout separation	2 mm rect.	
PEI	P.E.I.	4 (Tráfico: Medio - Alto)	
	Tono y Textura Mezclado / Mixed Tone and Texture	Medio / Medium	
	Resistencia al ataque químico / Chemical Resistance	Conforme / In compliance with	A.S.T.M. C650
	Coefficiente Dinámico de Fricción / DCOF	≥ 0.42 %	A.S.T.M. C1028
	Absorción de agua / Water absorption	≤ 3 %	A.S.T.M. C373
	MOHS	5 - 8	A.S.T.M. C1028
	Resistencia a la flexión / Breaking Strength	≥ 250kg / 551 lbs	ISO 10545-4
	Resistencia al shock térmico / Resistance to thermal shock	Conforme / In compliance with	A.S.T.M. C484
	Resistencia a helada / Resistance to frost	Conforme / In compliance with	A.S.T.M. C1026
	Resistencia a las manchas / Resistance to staining	Conforme / In compliance with	A.S.T.M. C1378
	Resistencia a la abrasión / Resistance to abrasion	Conforme / In compliance with	ANSI A137

Cesantoni S.A. de C.V. certifica que los resultados anteriores fueron obtenidos en análisis de laboratorio elaborado por el departamento de Control de Calidad.
Cesantoni certifies that all results were obtained on a laboratory testing by quality control department.

www.cesantoni.com.mx

contacto@cesantoni.com.mx

 **TCNA**
Tile Council of North America, Inc.